

# PRODUCT DATA SHEET

## Acrylic Elastic Waterproof Coating

### INTRODUCTION

Acrylic Elastic Waterproof Coating is a single-component emulsion-type waterproof coating formulated with pure acrylic polymer emulsion and other additives. Once cured, the waterproof coating forms a waterproof membrane with extensibility, plasticity, crack resistance, and weather resistance, providing functions such as waterproofing, seepage prevention, and protection. This coating has good temperature adaptability, is easy to use, and is convenient for maintenance and repair.

### APPLICATION

1. Building Surfaces: Roofs and terraces, Interior and, exterior walls, Balconies.
2. Indoor Spaces: Bathrooms, Warehouses, Kitchens.
3. Special Structures: Basements, Pools, Water tanks.
4. Infrastructure: Tunnels, Bridges, Reservoirs.

Note:

1. This product can be exposed to the sunshine and is UV resistant.
2. This product can be used in areas with heavy water accumulation. It can be submerged in water for 20 days without peeling or falling off, but it cannot be submerged in water for a year.
3. When used in swimming pools or water tanks, a layer of concrete topping or tile topping is required.
4. This product can adhere to surfaces such as concrete, metal, tiles, glass, wood, and other coatings.
5. Application methods: Applying with a sprayer, roller, brush, or scraper.
6. This product can also be diluted with water for use.
7. This product can be used with fiber mesh.

### ADVANTAGES

- **Excellent Weather Resistance:** It has superior weather resistance, heat resistance, and UV resistance, remaining stable within the temperature range of -30 to 80 degrees Celsius.
- **High Elasticity:** It has good extensibility, suitable for minor cracks and deformations of the substrate.
- **Customizable colors:** It can be made in various colors.

- **Environmentally Friendly:** The material is eco-friendly and non-toxic, harmless to humans.
- **Easy to Apply:** It is easy to apply, with a short construction period and convenient maintenance.
- **Good Breathability:** Suitable for wet substrates with excellent breathability.

### PACKAGING & COVERAGE

|                         |                                                                                     |
|-------------------------|-------------------------------------------------------------------------------------|
| <b>Specification:</b>   | 18kg/pail or 50kg/pail                                                              |
| <b>Appearance:</b>      | Single component, viscous liquid, default color is white, color can be customized.  |
| <b>Coverage:</b>        | It is recommended to apply two coats, with each pail covering 13~15m <sup>2</sup> . |
| <b>Warranty period:</b> | Normal Quality: 6~8 years.<br>Excellent Quality: more than 10 years.                |
| <b>Shelf Life:</b>      | 1 Year                                                                              |

### CONSTRUCTION STEPS

#### 1. Surface Preparation

The substrate must be solid, level, free of dust, oil, and dry before application.

Clean and sweep the surface thoroughly before starting. Fill cracks and grooves around pipe roots with a non-shrink grout until smooth.

#### 2. Detailing Waterproof Treatment

Prior to applying the primary waterproofing layer, apply 2~3 coats of this product to corners, pipe penetrations, and drain areas to create an additional waterproofing barrier, with a film thickness of no less than 0.8mm.

#### 3. Coating Application

Apply the waterproof coating evenly onto the substrate using a roller or brush. A minimum of two coats is recommended, achieving a total dry film thickness of at least 0.8mm. Ensure the second coat is applied perpendicular to the first. Allow a 3-5 hour interval between coats, and proceed only when the previous coat is tack-free. For enhanced strength, the coating can be reinforced with fiber mesh.

This product is also suitable for spray application and can be diluted with water.

#### 4. Vertical Surface Treatment

## PRODUCT DATA SHEET

If plastering is required on wall panels, sprinkle a small amount of clean stone chips or fine sand onto the final uncured coating layer to enhance adhesion with the cement mortar.

### 5. Protective Layer Application (Optional)

This product can be used outdoors, such as on roofs, walls, etc. It can be directly exposed to sunlight and even withstand small areas of standing water, so no protective covering is required. However, if the product is used in swimming pools, bathrooms, floors, etc., a protective layer such as mortar, tiles, etc., must be applied over the waterproof coating after it has dried.

#### Note:

1. Do not apply during rainy conditions. The product must not come into contact with water before it is completely dry, and rain should be avoided within 24 hours after application.
2. Application can proceed even when the substrate is slightly damp, as this is a water-based waterproofing product. However, no standing water should be present on the surface.
3. It is recommended to apply the product at temperatures

between 5°C and 35°C. Within this temperature range, the material can form a proper film, ensuring optimal adhesion, flexibility, and waterproofing performance.

### HANDLING & HEALTH

1. Please wear rubber or plastic gloves to avoid contact with skin.
2. Product is for professional use only.
3. If the product comes into contact with skin during application, it can be removed by rinsing the affected area with clean water.

### STORAGE & SAFETY

1. This product is eco-friendly and non flammable.
2. This product must be stored dry, protected from sun and rain.
3. This product should not be stored at temperatures below 5°C. As a water-based waterproof coating, it may freeze at low temperatures, which can compromise product quality.

### TECHNICAL DATA

| No. | Test Item                                     | Standard Requirements                         | Test Results                                  | Individual Results |      |
|-----|-----------------------------------------------|-----------------------------------------------|-----------------------------------------------|--------------------|------|
| 1   | Appearance                                    | Easy to mix without lumps, in a uniform state | Easy to mix without lumps, in a uniform state | Pass               |      |
| 2   | Impermeability                                | 0.3 MPa, 30 minutes impermeable               | 0.3 MPa, 30 minutes impermeable               | Pass               |      |
| 3   | Tensile Strength (MPa)                        | ≥1.0                                          | 1.3                                           | Pass               |      |
| 4   | Elongation at Break (%)                       | ≥300                                          | 452                                           | Pass               |      |
| 5   | Solid Content (%)                             | ≥65                                           | 73                                            | Pass               |      |
| 6   | Low-Temperature Flexibility                   | No Cracking at -10°C                          | No Cracking                                   | Pass               |      |
| 7   | Drying Time                                   | Surface Drying                                | ≤4                                            | 3                  | Pass |
|     |                                               | Thorough Drying                               | ≤8                                            | 7                  | Pass |
| 8   | Heating elongation, %                         | Elongation                                    | ≤ 1.0                                         | -                  | Pass |
|     |                                               | Shortening                                    | ≤ 1.0                                         | 0.5                | Pass |
| 9   | Tensile strength retention after treatment, % | Heat Treatment                                | ≥80                                           | 92                 | Pass |
|     |                                               | Alkaline Treatment                            | ≥60                                           | 77                 | Pass |
|     |                                               | Acid Treatment                                | ≥40                                           | 62                 | Pass |
| 10  | Elongation at break after treatment, %        | Heat Treatment                                | ≥200                                          | 256                | Pass |
|     |                                               | Alkaline                                      | ≥200                                          | 225                | Pass |

## PRODUCT DATA SHEET



|    |          |                |              |      |
|----|----------|----------------|--------------|------|
|    |          | Treatment      |              |      |
|    |          | Acid Treatment | ≥200         | 222  |
|    |          |                |              | Pass |
| 11 | VOC, g/L | ≤10            | not detected | Pass |

### LEGAL NOTICE

*This document is based on Boslai's current product knowledge and assumes proper storage, handling, and application under normal conditions. Due to variations in materials and site conditions, no warranties —express or implied— are provided. Users must verify suitability. Boslai reserves the right to modify products and specifications. Third-party IP rights apply. Orders follow current sales terms. For the latest technical datasheet, contact us.*